



**RAMSAUER®**  
**DICHTSTOFFE**

# 1260 FLEXBAND PRO

**(Flexible tape)**

## TECHNICAL DATA

Colour: grey  
Thickness: 0.60 mm  
Width: 120 mm  
Weight: 50 g/m  
Resistance to water pressure: tight at 3 bars  
Transverse elongation: 250 %  
Longitudinal elongation: 50 %  
Temperature resistance: -20°C to +90°C  
Storage life: 24 months in a cool and dry place in original carton  
Packaging: 1 roll of 50 m in a carton, 120 cartons on a pallet.

## CHARACTERISTICS

Elastic sealing tape on an NBR-rubber basis with a woven-fabric-free zone and nonwoven coating layers on both sides. The elastic recovery of 1260 FLEXBAND PRO is excellent.

## APPLICATIONS

For forming corners and bridging joints in composite sealing according to the instruction sheet of the Central Association of the German Building Industry ("ZDB-Merkblatt"); for all moisture stress classes according to the ZDB Instruction Sheet and according to the German General Building Inspection Test Certificate ("AbP"). Suitable for composite sealing in balconies, loggias and arcades according to DIN



18531, indoor sealing according to DIN 18534, as well as in containers and basins according to DIN 18535. The product meets the requirements of Austrian standard ÖNORM B 3407 up to stress class W6.

## PREPARATION OF THE SUBSTRATE

The required preparation of the substrate depends on the type and characteristics of the substrate and the intended sealing system. It is imperative to apply a suitable primer (see

application table). After the primer has dried cover a strip reaching approx. 5 cm beyond the 1260 FLEXBAND PRO tape with the sealing compound.

## PROCESSING

Cut 1260 FLEXBAND PRO to the required length and insert into the fresh liquid seal which serves as an adhesion promoter. Make sure that the sealing tapes overlap by at least 5 cm. Any uneven spots or cracks can be levelled out or removed by

means of a smoothing trowel. Finally apply 2 to 3 paint coats over the entire surface, thereby covering 1260 FLEXBAND PRO completely.

## CONSUMPTION

Take into account a minimum overlapping of 5 cm.

## ADVICE FOR SUBSEQUENT WORK

Thanks to the starting materials used, this product is compatible with polymer dispersions, flexible mineral slurry seals, and

reactive resins. Before applying any additional layers it is recommended to make a compatibility test.

## CLEANING TOOLS AND EQUIPMENT

Tools and contaminated areas must be cleaned with water immediately after using the product.

## HAZARD WARNINGS

This product is not a hazardous substance within the meaning of the German Hazardous Substances Ordinance

("Gefahrstoffverordnung").

## SAFETY AND DISPOSAL ADVICE

Consult the current EC Safety Data Sheet which is available at any time on our website at [www.ramsauer.at](http://www.ramsauer.at).

## LIABILITY FOR DEFECTS

1260 FLEXBAND PRO / Version: 01/17

Page:1

Supersedes version: 02/16

Ramsauer GmbH & Co KG, 4822 Bad Goisern am Hallstätter See, Sarstein 17, Austria

Phone: +43 (0)6135 8205-0, Fax: +43 (0)6135 8323 - Email: [office@ramsauer.at](mailto:office@ramsauer.at) - Internet: [www.ramsauer.at](http://www.ramsauer.at)



**RAMSAUER®**  
**DICHTSTOFFE**

The information provided including but not limited to the proposals for processing and using our products is based on our knowledge and experience, usually at the time of going into print. The results of work may deviate from this information depending on the specific circumstances, in particular with respect to substrates, processing and environmental conditions. Therefore, neither this information nor any oral counselling shall constitute warranty or give rise to any liability on whatever legal ground for any specific result

of work, unless we acted intentionally or by gross negligence. Ramsauer warrants that its products will have the technical characteristics according to the Technical Data Sheets up to their expiry date.

Product users must consult the latest data sheet which is available upon request. Our current General Terms and Conditions apply which are available for download on our website [www.ramsauer.at](http://www.ramsauer.at).



**QUALITY YOU CAN RELY ON**

**Ramsauer GmbH & Co KG, 4822 Bad Goisern/Hallstätter See, Sarstein 17, Austria**

Phone: +43 (0)6135 8205-0, Fax: +43 (0)6135 8323 - Email: [office@ramsauer.at](mailto:office@ramsauer.at) - Internet: [www.ramsauer.at](http://www.ramsauer.at)